

POLYBOND[®] 7200

Developmental Polymer Modifier

POLYBOND[®] 7200 is a maleic anhydride modified polypropylene homopolymer.

CAS Number 9003-07-0

Typical Physical Properties¹ of POLYBOND[®] 7200

Property	Typical Value	Test Based On
Appearance	Off-white Pellet	Visual
Melt Flow Rate @ 190°C, 2.16Kg	250 g/10 min	ASTM D-1238
Maleic Anhydride Content	Very High ²	ASTM D-6047
Density @ 23°C	0.91 g/cm ³	ASTM D-792
Bulk Density	0.6 g/cm ³	ASTM D-1895B
Melting Point	160-170°C	DSC

1. Developmental Product – When commercialized, properties may not be identical to those reported above.

2. Very High = Maleic Anhydride Content typically in the range of 1.5 to 1.9%.

Applications

- Additive for non-woven polypropylene providing improved adhesion to printing inks when used with a primer
- High efficiency coupling agent for cellulose fiber-filled polypropylene leading to reduced water uptake and higher flexural/tensile strengths
- Coupling agent for mineral-filled polypropylene offering improved strength and impact properties

Food Contact

For details please contact AddivantTM Regulatory Affairs

Regulatory Status

The components of POLYBOND[®] 7200 are listed on USA TSCA inventory. For information on other inventory listings, see Section 15 (Regulatory Information) of the MSDS for POLYBOND[®] 7200.

Storage & Handling Precautions

Keep POLYBOND[®] 7200 dry prior to processing. Loss of anhydride functionality may occur due to conversion to acid groups by reaction with atmospheric moisture. Tie liners of open boxes when not in use to prevent exposure to moisture. If exposure occurs, POLYBOND[®] 7200 can be dried in a hopper dryer or oven for three hours at 105°C to remove moisture. A slight pungent odor is normal during processing of POLYBOND[®] 7200. Purge equipment with polypropylene before and after running POLYBOND[®] 7200.

For additional handling and toxicological information consult the AddivantTM Material Safety Data Sheet

The information contained herein relates to a specific AddivantTM product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of AddivantTM standard terms and conditions of sale under which the product is sold by AddivantTM. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND ANY AND ALL SUCH REPRESENTATIONS AND WARRANTIES ARE HEREBY EXPRESSLY DISCLAIMED. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

AddivantTM is a trademark of Addivant USA, LLC or one of its affiliates.

Copyright © 2013 Addivant USA, LLC. All rights reserved.