

**IMUTHANE**  
CASTABLE POLYURETHANE  
ELASTOMERS  
**32-90A****IMUTHANE**  
**32-90A**

IMUTHANE 32-90A is a TDI / PPG based prepolymer which yields 90 Shore-A elastomer when cured with 4, 4' methylene bis ortho chloroaniline (MBOCA).

**Typical Prepolymer Properties**

% NCO	5.3 – 5.7
Brookfield Viscosity @ 100° C	1.0 – 2.5
Specific Gravity @ 77° F (25° C)	1.08
@ 212° F (100° C)	1.02

**Typical Process Conditions**

IMUTHANE 32-90A, °F (°C)	150 (66)
MBOCA, °F (°C)	240 (115)
Mold, °F (°C)	212 (100)
% Theory	90
Pot Life, min	5
Cure Time, min @ °F (°C)	60 @ 212 (100)
Post Cure, hrs @ °F (°C)	16 @ 158 (70)

**Typical Physical Properties**

Shore Hardness	90A
100% Modulus, psi (MPa)	1200 (8.3)
300% Modulus, psi (MPa)	2200 (15.2)
Tensile, psi (MPa)	3300 (22.8)
Elongation, %	375
Tear Strength, Die C, pli (kN/m)	350 (61.3)
Tear Strength, (D470), pli (kN/m)	70 (12.3)
Bashore Rebound, %	30
Compression Set, Method B, 22 hrs @ 158°F (70°C), %	40
Specific Gravity	1.13

The data contained herein are believed to be reliable. However, there is no guarantee that the same results will be obtained under different conditions. Fit for use testing should be conducted by each user.