

**IMUTHANE**
CASTABLE POLYURETHANE
ELASTOMERS
32-93A**IMUTHANE**
32-93A

IMUTHANE 32-93A is a TDI / PPG based prepolymer which yields 93 Shore-A elastomer when cured with 4, 4' methylene bis ortho chloroaniline (MBOCA).

Typical Prepolymer Properties

% NCO	6.1 – 6.5
Brookfield Viscosity @ 100° C	0.7 – 1.6
Specific Gravity @ 77° F (25° C)	1.08
@ 212° F (100° C)	1.02

Typical Process Conditions

IMUTHANE 32-93A, °F (°C)	140 (60)
MBOCA, °F (°C)	240 (115)
Mold, °F (°C)	212 (100)
% Theory	90
Pot Life, min	4
Cure Time, min @ °F (°C)	60 @ 212 (100)
Post Cure, hrs @ °F (°C)	16 @ 158 (70)

Typical Physical Properties

Shore Hardness	93A
100% Modulus, psi (MPa)	1500 (10.3)
300% Modulus, psi (MPa)	2500 (17.2)
Tensile, psi (MPa)	4000 (27.6)
Elongation, %	400
Tear Strength, Die C, pli (kN/m)	375 (65.7)
Tear Strength, (D470), pli (kN/m)	80 (14.0)
Bashore Rebound, %	30
Compression Set, Method B, 22 hrs @ 158°F (70°C), %	40
Specific Gravity	1.13

The data contained herein are believed to be reliable. However, there is no guarantee that the same results will be obtained under different conditions. Fit for use testing should be conducted by each user.